

The Goodyear Tire & Rubber Company

Akron, Ohio 44316-0001

Intellectual Property Law Department

Facsimile Transmission

This transmittal is strictly intended for delivery only to the person listed below. It may contain confidential or privileged information, the disclosure of which is prohibited. If you have received this facsimile and are not the intended recipient, you are hereby notified that the copying, distribution, or other unauthorized use of this communication is prohibited. If you have received this communication in error, please notify us immediately by telephone to arrange for return of the document

Date: September 24, 2003

To: Examiner Medley

Fax #: 817038729651

From: Henry C. Young, Jr., Esq.
The Goodyear Tire & Rubber Company
1144 East Market Street - D/823
Akron, Ohio 44316-0001
(330) 796-2956
henry.young@goodyear.com

Number of pages transmitted: 2
INCLUDING this cover sheet

If problems with transmission, please call number above.

Message:

For: Serial No.: 10/037,539; Attorney Docket No.: DN2001214; Confirmation No.: 7282

Per our telephone conversation today, the following is a copy of Page 32 from the specification as filed for the above noted patent application.

Please feel free to contact me should you have any questions or need additional information. Thank you for your assistance in this matter.

STREET ADDRESS: 1144 EAST MARKET STREET, AKRON OH 44316-0001
TELEPHONE: (330) 796-4787 FACSIMILE: (330) 796-9018 (330) 796-2061

- 32 -

9. The process of claim 1 wherein said process further comprises:

(A) using an emulsion stabilizing amount of said cationic surfactant in said latex for said polymerization of said monomers to prevent coagulation of resultant elastomer particles from said latex,

5 (B) following completion of said polymerization of said monomers, adding an increased amount of the same or additional cationic surfactant to said latex to increase the amount of cationic surfactant available for ion exchange with cationic exchangeable ions contained in the galleries of said water-swellaable clay, and thereafter,

(C) blending said resulting latex with said water-swellaable clay in an amount
10 of said clay based upon substantially equivalent cationic ions of total of said cationic surfactant(s) to said cationic ion exchangeable ions in said galleries of said clay.

10. The process of claim 1 wherein said water swellaable clays are selected from at least one of water-swellaable smectite clays, vermiculite based clays and mica
15 based clays.

11. The process of claim 1 wherein said water-swellaable clay is a smectite clay selected from at least one of montmorillonite, hectorite, nontrite, beidellite, volkonskoite, saponite, sauconite, sobockite, sterensite, and sinfordite clays.
20

12. The process of claim 1 wherein ions contained in the galleries of said water-swellaable clay between its platelets are comprised of at least one of sodium ions and potassium ions.

25 13. A nanocomposite prepared by the process of claim 1.

14. A nanocomposite prepared by the process of claim 9.

15. A rubber composite comprised of a blend of said nanocomposite of claim
30 13 and additional elastomer(s) and/or additional particulate reinforcing filler.

16. A rubber composite comprised of a blend of said nanocomposite of claim 14 and additional elastomer(s) and/or additional particulate reinforcing filler.